

Tensile Test, 75K, ASTM A370, Longitudinal, room temperature, on QTC, per batch						
	Yield Strength at 0.2%		Tensile Strength		Elongation	Reduction in Area
	psi	MPa	psi	MPa	%	%
Min.	75 000	517	95 000	517	18	35

Impact Test, ASTM A370, Charpy V notch, Longitudinal, Temperature - 75°F (- 60°C), on QTC, per batch
Min. Average 20 ft-lb (27 J) and only one single less than 20 ft-lb (27 J) and min. 15 ft-lb (20 J) Min. Lateral Expansion 0.015 in. (0.38 mm)

Surface Hardness test on each product
Min: 207 HB - Max: 234 HB (22HRC)

### NON-DESTRUCTIVE EXAMINATIONS

Ultrasonic and surface defect inspections are performed on each product, in accordance with API Spec. 6A procedures.

### FINISH AND APPEARANCE

Finish and appearance of our products comply with ASTM A322.